

Cone Conversion

Cone	Degrees
019	1252 *F
018	1319 *F
017	1360 *F
016	1422 *F
015	1456 *F
014	1485 *F
013	1539 *F
012	1582 *F
011	1607 *F
010	1657 *F
09	1688 *F
08	1728 *F
07	1789 *F
06	1828 *F
05	1888 *F
04	1945 *F

Cone 04 is not the same as cone 4!
The Scale runs Cone 04, 03, 02, 01, 0, 1, 2, 3, 4...
Cone 4 is OVER 2000*F!

***Cones are designed to describe how fluid heat has made ceramic. This chart is a generalization of the temperature at which cone effects are achieved when firing slowly. When in doubt watch your kiln!